

Safety Data Sheet

Page 1 of 8

SDS No.: 168444

V001.2

Revision: 10.02.2019 printing date: 23.06.2023

LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL SEALANT 310 G

SECTION 1 IDENTIFICATION OF THE MATERIAL AND SUPPLIER

Product name: LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL

SEALANT 310 G

Intended use: Sealant

Supplier:

Henkel New Zealand Ltd 2 Allens Rd Auckland, 2013 New Zealand

Phone: +64 (9) 272-6710

Emergency information: 24 HOUR EMERGENCY CONTACT NUMBER 0800 243 622

SECTION 2 HAZARDS IDENTIFICATION

Classification of the substance or mixture HSNO Classification:

8.2B Class 8 - Corrosiveness, Subclass 8.2 - Skin corrosive, Hazard Classification B Class 8 - Corrosiveness, Subclass 8.3 - Eye corrosive, Hazard Classification A

GHS Classification:

Hazard ClassHazard CategorySkin corrosionCategory 1BSerious eye damage/eye irritationCategory 1

Hazard pictogram:

Signal word: Danger

LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL SEALANT 310 G

Hazard statement(s): H314 Causes severe skin burns and eye damage.

Precautionary Statement(s):

Prevention: P260 Do not breathe dusts or mists.

P264 Wash hands thoroughly after handling.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

Response: P301+P330+P331 IF SWALLOWED: Rinse mouth. Do NOT induce vomiting.

P303+P361+P353 IF ON SKIN (or hair): Take off immediately all contaminated clothing.

Rinse skin with water [or shower].

P304+P340+P310 IF INHALED: Remove victim to fresh air and keep at rest in a position

comfortable for breathing. Immediately call a POISON CENTER or physician. P305+P351+P338+P315 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Get immediate medical

advice/attention.

P363 Wash contaminated clothing before reuse.

Storage: P405 Store locked up.

Disposal: P501 Dispose of contents/container to an appropriate treatment and disposal facility in

accordance with applicable laws and regulations.

SECTION 3 COMPOSITION/INFORMATION ON INGREDIENTS

General chemical description: Mixture

Type of preparation: Acetoxy curing silicone

Identity of ingredients:

Chemical ingredients	CAS-No.	Proportion
Hydrocarbon C11-25 dearomatized	64742-46-7	10- < 30 %
Methylsilanetriyl triacetate	4253-34-3	10- < 30 %
Triacetoxyethylsilane	17689-77-9	10- < 30 %

SECTION 4 FIRST AID MEASURES

Ingestion: Do not induce vomiting.

Seek medical advice.

Skin: Rinse with running water and soap.

Obtain medical attention if irritation persists.

Eyes: Rinse immediately with plenty of running water (for 10 minutes). Seek medical attention if

necessary.

Inhalation: Move to fresh air. If symptoms persist, seek medical advice.

First Aid facilities: Eye wash

Normal washroom facilities

Medical attention and special

treatment:

Treat symptomatically and supportively.

LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL SEALANT 310 G

SECTION 5. FIRE FIGHTING MEASURES

Suitable extinguishing media: Carbon dioxide, foam, powder

Fine water spray

Decomposition products in case of

fine.

carbon oxides. Silica fume

Special protective equipment for

fire-fighters:

Wear self-contained breathing apparatus.

Additional fire fighting advice: In case of fire, keep containers cool with water spray.

Hazchem code: 2X

SECTION 6. ACCIDENTAL RELEASE MEASURES

Personal precautions: Avoid contact with skin and eyes.

Ensure adequate ventilation.

Environmental precautions: Do not let product enter drains.

Clean-up methods: Scrape up as much material as possible.

Ensure adequate ventilation.

Store in a partly filled, closed container until disposal.

SECTION 7. HANDLING AND STORAGE

Precautions for safe handling: Use only in well-ventilated areas.

Vapours should be extracted to avoid inhalation.

Conditions for safe storage: Store in a cool, well-ventilated place.

Never allow product to get in contact with water during storage

SECTION 8. EXPOSURE CONTROLS / PERSONAL PROTECTION

Workplace exposure standards:

Ingredient [Regulated substance]	form of exposure	TWA (ppm)	TWA (mg/m3)	Ceiling	STEL (ppm)	STEL (mg/m3)
OIL MIST, MINERAL 64742-46-7	Mist.		5		-	
OIL MIST, MINERAL	Mist.	_	-	-		10

Engineering controls: Use only with adequate ventilation.

Eye protection: Wear protective glasses.

Skin protection:

The use of chemical resistant gloves such as Nitrile is recommended.

Please note that in practice the working life of chemical resistant gloves may be considerably reduced as a result of many influencing factors (e.g. temperature). Suitable risk assessment should be carried out by the end user. If signs of wear and tear are noticed

then the gloves should be replaced.

Respiratory protection: Use only in well-ventilated areas.

If inhalation risk exists, wear a respirator or air supplied mask complying with the

requirements of AS/NZS 1715 and AS/NZS 1716.

LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL SEALANT 310 G

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

red Appearance:

paste Acetic acid Odor: Specific gravity: 1.05

Flash point: > 93 °C (> 199.4 °F)

(Tagliabue closed cup)

Lower explosive limit: 4 %(V)

(acetic acid) 19.9 %(V)

Upper explosive limit: (acetic acid) < 10 mm hg

Vapor pressure:

(; 20 °C (68 °F))

Insoluble

Solubility in water: **VOC** content: 4.8 % 50.4 g/l

SECTION 10. STABILITY AND REACTIVITY

Conditions to avoid: Stable under normal conditions of storage and use.

Incompatible materials: Acids.

Bases.

Oxidizing agents.

Polymerises in presence of water.

Hazardous decomposition

products:

Acetic acid is liberated slowly upon contact with moisture.

Hazardous polymerization: Will not occur.

SECTION 11 TOXICOLOGICAL INFORMATION

Health Effects:

Ingestion: Ingestion of large amounts may produce gastrointestinal disturbances including irritation, nausea,

and diarrhea.

Skin: Causes skin burns.

Eves: Contact with this product may cause severe eye damage.

Inhalation: Acetic acid produced during cure may irritate eyes, nose and throat.

Chronic effects: No chronic health effects are expected from the intended use of these products or from

foreseeable handling of them in the workplace.

Acute toxicity:

Hazardous components	Value	Value	Route of	Exposure	Species	Method
CAS-No.	type		application	time		
Hydrocarbon C11-25	LD50	> 5,000 mg/kg	oral		rat	OECD Guideline 401 (Acute
dearomatized	LC50	> 5.266 mg/l	inhalation	4 h	rat	Oral Toxicity)
64742-46-7	LD50	> 2,000 mg/kg	dermal		rabbit	not specified
						OECD Guideline 402 (Acute
						Dermal Toxicity)
Methylsilanetriyl	LD50	1,600 mg/kg	oral		rat	OECD Guideline 401 (Acute
triacetate						Oral Toxicity)
4253-34-3						
Triacetoxyethylsilane	LD50	1,460 mg/kg	oral		rat	OECD Guideline 401 (Acute
17689-77-9						Oral Toxicity)

LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL SEALANT 310 G

Skin corrosion/irritation:

Hazardous components CAS-No.	Result	Exposure time	Species	Method
Methylsilanetriyl triacetate 4253-34-3	corrosive	4 h	rabbit	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)
Triacetoxyethylsilane 17689-77-9	Category 1B (corrosive)	3 min	rabbit	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)

Serious eye damage/irritation:

Hazardous components	Result	Exposure	Species	Method
CAS-No.		time		
Methylsilanetriyl	Category 1 (irreversible effects on the eye)		rabbit	OECD Guideline 405 (Acute
triacetate				Eye Irritation / Corrosion)
4253-34-3				

${\bf Respiratory\ or\ skin\ sensitization:}$

Hazardous components CAS-No.	Result	Test type	Species	Method
Methylsilanetriyl triacetate 4253-34-3	not sensitising	Guinea pig maximisat ion test	guinea pig	OECD Guideline 406 (Skin Sensitisation)
Triacetoxyethylsilane 17689-77-9	not sensitising	Guinea pig maximisat ion test	guinea pig	OECD Guideline 406 (Skin Sensitisation)

Germ cell mutagenicity:

Hazardous components	Result	Type of study /	Metabolic	Species	Method
CAS-No.		Route of administration	activation / Exposure time		
Methylsilanetriyl triacetate 4253-34-3	negative negative negative	bacterial reverse mutation assay (e.g Ames test) in vitro mammalian chromosome aberration test mammalian cell gene mutation assay	with and without with and without with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay) OECD Guideline 473 (In vitro Mammalian Chromosome Aberration Test) OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
Triacetoxyethylsilane 17689-77-9	negative negative negative	bacterial reverse mutation assay (e.g Ames test) in vitro mammalian chromosome aberration test mammalian cell gene mutation assay	with and without with and without with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay) OECD Guideline 473 (In vitro Mammalian Chromosome Aberration Test) OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)

Repeated dose toxicity:

Hazardous components CAS-No.	Result	Route of application	Exposure time / Frequency of treatment	Species	Method
Methylsilanetriyl triacetate 4253-34-3	NOAEL=50 mg/kg	oral: gavage	28-51 ddaily	rat	OECD Guideline 422 (Combined Repeated Dose Toxicity Study with the Reproduction / Developmental Toxicity Screening Test)

SECTION 12.

LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL SEALANT 310 G

General ecological information: Cured Loctite products are typical polymers and do not pose any immediate

environmental hazards., In the cured state contribution of this product to

Environmental Hazards is insignificant in comparison to articles in which it is used., Precautions required with respect to Environmental Hazards of articles in which this

product is used should be considered.

Toxicity:

Hazardous components	Value	Value	Acute	Exposure	Species	Method
CAS-No.	type		Toxicity Study	time		
Hydrocarbon C11-25 dearomatized	LC50	> 10,000 mg/l	Fish	96 h	Pimephales promelas	OECD Guideline 203 (Fish, Acute
64742-46-7 Methylsilanetriyl triacetate 4253-34-3	LC50	> 110 mg/l	Fish	96 h	Oncorhynchus mykiss	Toxicity Test) OECD Guideline 203 (Fish, Acute
Triacetoxyethylsilane 17689-77-9	LC50	251 mg/l	Fish	96 h	Brachydanio rerio (new name: Danio rerio)	Toxicity Test) OECD Guideline 203 (Fish, Acute
Triacetoxyethylsilane 17689-77-9	EC50	62 mg/l	Daphnia	48 h	Daphnia magna	Toxicity Test) OECD Guideline 202 (Daphnia sp.
						Acute Immobilisation Test)
Triacetoxyethylsilane 17689-77-9	IC50	73 mg/l	Algae	72 h	Scenedesmus subspicatus (new name: Desmodesmus subspicatus)	OECD Guideline 201 (Alga, Growth Inhibition Test)

Persistence and degradability:

Hazardous components CAS-No.	Result	Route of application	Degradability	Method
Hydrocarbon C11-25 dearomatized 64742-46-7		aerobic	30 %	OECD Guideline 301 D (Ready Biodegradability: Closed Bottle Test)
Triacetoxyethylsilane 17689-77-9			74 %	OECD Guideline 301 A (old version) (Ready Biodegradabiltiy: Modified AFNOR Test)

Bioaccumulative potential / Mobility in soil:

Hazardous components	LogPow	Bioconcentration	Exposure	Species	Temperature	Method
CAS-No.		factor (BCF)	time			
Triacetoxyethylsilane	0.74					not specified
17689-77-9						

SECTION 13. DISPOSAL CONSIDERATIONS

Waste disposal of product: Follow all local, state, federal and provincial regulations for disposal.

Cured rubber can be incinerated or landfilled following EPA and local regulations.

Disposal for uncleaned package: After use, tubes, cartons and bottles containing residual product should be disposed of as

chemically contaminated waste in an authorised legal land fill site or incinerated.

Disposal must be made according to official regulations.

SECTION 14. TRANSPORT INFORMATION

Page 7 of 8

SDS No.: 168444 V001.2

LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL SEALANT 310 G

Land Transport:

UN no.: 1760

Proper shipping name: CORROSIVE LIQUID, N.O.S.

(Ethyltriacetoxysilane, Methyltriacetoxysilane)

Class or division: 8
Packing group: III
Hazchem code: 2X

Marine transport IMDG:

UN no.: 1760

Proper shipping name: CORROSIVE LIQUID, N.O.S.

(Ethyltriacetoxysilane, Methyltriacetoxysilane)

Class or division: 8
Packing group: III
EmS: F-A ,S-B

Seawater pollutant:

Air transport IATA:

UN no.: 1760

Proper shipping name: Corrosive liquid, n.o.s. (Ethyltriacetoxysilane, Methyltriacetoxysilane)

Class or division: 8
Packing group: III
Packing instructions (passenger) 852
Packing instructions (cargo) 856

SECTION 15.

REGULATORY INFORMATION

HSNO Approval Number: HSR002658

Site and Storage: Refer to the site and storage requirements for this Group Standard.

Refer to the HSNO controls for approved hazardous substances.

SECTION 16. OTHER INFORMATION

Abbreviations/acronyms: STEL - Short term exposure limit

TWA - Time weighted average

HSNO - Hazardous Substances and New Organisms

GHS: Globally Harmonized System CAS: Chemical Abstracts Service LD 50: Lethal Dose 50%

LC 50: Lethal Concentration 50%

IMDG: International Maritime Dangerous Goods code

IATA-DGR: International Air Transport Association – Dangerous Goods Regulations

Reason for issue: Reviewed SDS. Reissued with new date. involved chapters: 1 - 16

Page 8 of 8

SDS No.: 168444 V001.2

LOCTITE SI 596 HIGH TEMP SIL SEALANT RED known as HIGH TEMP RED SIL SEALANT 310 G

Date of previous issue: 25.07.2017

Disclaimer:

The percentage weight (% w/w) of ingredients is not to be taken as a specification guaranteed by Henkel New Zealand Limited, but only as an approximate guide to the content of hazardous ingredients in the material. The information contained herein does not constitute a guarantee by Henkel New Zealand Limited concerning the properties of the material.

The information contained in this Safety Data Sheet is offered in good faith and has been developed from what is believed to be accurate and reliable sources. The information is offered without warranty, representation, inducement or licence and Henkel New Zealand Limited assumes no legal responsibility for reliance upon same. Henkel New Zealand Limited disclaims any liability for loss, injury or damage incurred in connection with the use of the material or its associated Safety Data Sheet.

This information is not to be construed as a representation that the material is suitable for any particular purpose or use except those conditions and warranties implied by Government statutes. Customers are encouraged to make their own enquiries as to the material's characteristics and, where appropriate, to conduct their own tests in the specific context of the material's intended use.

No warranty or representation of any kind is given with respect to the substantive or export laws of any other jurisdiction or country. Please confirm that the information provided herein conforms to the substantive export or other law of any other jurisdiction prior to export. Please contact Henkel Product Safety and Regulatory Affairs for additional assistance.